

AMENDMENTS TO THE CLAIMS

Please cancel claims 10-12 and 16-17. Please amend claims 5, 19, and 66.

Claim 1 (previously presented): A recyclable adhesive or adhesive coating comprising a polymer which is soluble or dispersible in water, wherein the polymer has 5 to 40 mol % of cationic repeat units, and wherein the adhesive or coating is attracted to fibers during paper recycling.

Claim 2 (previously presented): The recyclable adhesive or adhesive coating of claim 1, wherein the adhesive is substantially tacky such that it forms a pressure-sensitive adhesive which is capable of bonding to a surface upon contact.

Claim 3 (withdrawn): The recyclable adhesive or adhesive coating of claim 1, wherein the adhesive is a hot-melt adhesive capable of bonding to a surface when heated to above its melting point temperature.

Claim 4 (withdrawn): The recyclable adhesive or adhesive coating of claim 3, wherein the hot melt adhesive is formed by reacting polyamide with epichlorohydrin.

Claim 5 (currently amended): The recyclable adhesive or adhesive coating of claim 1, wherein the polymer comprises a cationically charged monomer of 3-(methacrylamino) propyltrimethyl-ammonium chloride and a backbone of n-butyl acrylate co-polymerizable with the cationically charged monomer.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 6 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the backbone is present in the amount of 60 to 95 mole % based on the polymer.

Claim 7 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the backbone is present in the amount of 80 to 90 mole % based on the polymer.

Claim 8 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the cationically charged monomer is present in the amount of 5 to 40 mole % based on the polymer.

Claim 9 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the cationically charged monomer is present in the amount of 8 to 25 mole % based on the polymer.

Claims 10-12 (canceled).

Claim 13 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the polymer further comprises an internal cross-linker present in the amount of up to 2 mole %, based on the polymer.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 14 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the polymer further comprises an internal cross-linker present in the amount of 0.1 to 1 mole %, based on the polymer.

Claim 15 (withdrawn): The recyclable adhesive or adhesive coating of claim 13, wherein the internal cross-linker is chosen from at least one of ethylene glycol dimethylate, diallyl maleate, diallyl phthalate, divinyl benzene, and poly(ethylene glycol) di(meth)acrylate.

Claims 16-17 (canceled).

Claim 18 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the polymer further comprises up to 35 mole % based on the polymer of an uncharged water soluble monomer or macromer.

Claim 19 (withdrawn): The recyclable adhesive or adhesive coating of claim 18, wherein the uncharged water soluble monomer or macromer is chosen from at least one of dialkylaminoethyl methacrylate, hydroxy alkyl (meth)acrylate, hydroxy [[alkyl]] alkyl vinyl ether, poly(ethylene glycol) (meth)acrylate, polyethylene glycol, glycerol, diethylenetriamine.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 20 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the adhesive further comprises a plasticizer to increase the flexibility of the adhesive.

Claim 21 (withdrawn): The recyclable adhesive or adhesive coating of claim 5, wherein the adhesive further comprises a tackifier to render the adhesive tacky.

Claim 22 (withdrawn): The recyclable adhesive or adhesive coating of claim 1, wherein the adhesive or adhesive coating forms a tape.

Claim 23 (withdrawn): The recyclable adhesive or adhesive coating of claim 1, wherein the adhesive or adhesive coating forms a label.

Claim 24 (withdrawn): The recyclable adhesive or adhesive coating of claim 1, wherein the adhesive or adhesive coating forms a paper coating.

Claim 25 (withdrawn): The recyclable adhesive or adhesive coating of claim 1, wherein the adhesive or adhesive coating forms a self-adhesive stamp.

Claim 26 (withdrawn): A method for making a recyclable adhesive or coating, comprising:

combining a cationically charged monomer and a backbone which is co-polymerizable with the cationically charged monomer to form a reaction mixture,

wherein the concentrations of the cationically charged monomer and the backbone are pre-selected to control the cationic content of the adhesive; and

polymerizing the reaction mixture to form an adhesive or coating comprising a polymer which is soluble or dispersible in water, wherein the polymer has 5 to 40 % of cationic repeat units such that the adhesive or coating is attracted to fibers during paper recycling.

Claim 27 (withdrawn): The method of claim 26, wherein polymerizing the reaction mixture is performed by emulsion polymerization, micro emulsion polymerization, miniemulsion polymerization, solution polymerization, condensation polymerization, or precipitation polymerization.

Claim 28 (withdrawn): The method of claim 26, wherein polymerizing the reaction mixture comprises heating the reaction mixture to a temperature sufficient to initiate polymerization of the reaction mixture.

Claim 29 (withdrawn): The method of claim 26, wherein the polymerizing is carried out in the presence of an initiator.

Claim 30 (withdrawn): The method of claim 26, further comprising adding an internal cross-linker to the reaction mixture prior to polymerizing the reaction mixture.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 31 (withdrawn): The method of claim 26, further comprising adding an uncharged water soluble monomer or macromer having a molecular weight of 350 to 3,000 prior to polymerizing the reaction mixture.

Claim 32 (withdrawn): The method of claim 26, further comprising adding deionized water to the reaction mixture prior to heating the reaction mixture, wherein heating the reaction mixture results in emulsion polymerization of the reaction mixture.

Claim 33 (withdrawn): The method of claim 26, further comprising adding an alcohol to the reaction mixture prior to heating the reaction mixture, wherein heating the reaction mixture results in solution polymerization of the reaction mixture.

Claim 34 (withdrawn): The method of claim 26, wherein the adhesive is substantially tacky such that it forms a pressure-sensitive adhesive which is capable of bonding to a surface upon contact.

Claim 35 (withdrawn): The method of claim 26, further comprising combining a tackifier with the polymer to render the adhesive substantially tacky.

Claim 36 (withdrawn): The method of claim 26, further comprising combining a plasticizer with the polymer for increasing the flexibility of the adhesive or coating.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 37 (withdrawn): The method of claim 26, wherein the polymer formed comprises 60 to 95 mole % of the backbone, wherein the backbone is selected from the group consisting of vinyl acetate, butadiene, styrene, acrylate comprising 1 to 8 carbon atoms in the alkyl group, and combinations of these compounds.

Claim 38 (withdrawn): The method of claim 27, wherein the polymer formed comprises 75 to 85 mole % of the backbone, wherein the backbone is selected from the group consisting of vinyl acetate, butadiene, styrene, acrylate comprising 1 to 8 carbon atoms in the alkyl group, and combinations of these compounds.

Claim 39 (withdrawn): The method of claim 37, wherein the backbone is an acrylate selected from the group consisting of n-butyl acrylate, 2-ethyl hexyl acrylate, and isooctyl acrylate.

Claim 40 (withdrawn): The method of claim 26, wherein the polymer formed comprises 5 to 40 mole % of the cationically charged monomer, the cationically charged monomer being selected from the group consisting of {3-methacryloylammino}propyl} trimethyl-ammonium chloride, {2-(methacryloyloxy) ethyl} trimethyl ammonium chloride, diallyldimethylammonium chloride, and vinyl benzyl trimethyl ammonium chloride.

Claim 41 (withdrawn): The method of claim 26, wherein the polymer formed comprises 10 to 25 mole % of the cationically charged monomer, the cationically charged monomer being selected from the group consisting of {3-

methacryloylammino)propyl} trimethyl-ammonium chloride, {2-(methacryloyloxy) ethyl} trimethyl ammonium chloride, diallyldimethylammonium chloride, cetylammonium bromide, and the reaction product of epichlorohydrin and trialkylamine or an amide.

Claim 42 (withdrawn): The method of claim 30, wherein the polymer formed comprises 0 to 2 mole %, preferably 0.1 to 1 mole %, of the internal cross-linker being selected from the group consisting of ethylene glycol dimethylate, diallyl maleate, diallyl phthalate, divinyl benzene, and poly(ethylene glycol) di(meth)acrylate.

Claim 43 (withdrawn): The method of claim 31, wherein the polymer formed comprises 0 to 35 mole % of the uncharged water soluble monomer or macromer.

Claim 44 (withdrawn): The method of claim 43, wherein the uncharged water soluble monomer or macromer is selected from the group consisting of , dialkylaminoethyl methacrylate, hydroxy alkyl (meth)acrylate, hydroxy alkyl vinyl ether, poly(ethylene glycol) (meth)acrylate, polyethylene glycol, glycerol, diethylenetriamine, polyethyleneimine, and combinations thereof.

Claim 45 (withdrawn): A method for recycling a paper product and a recyclable adhesive or coating, comprising repulping the paper product by placing the paper product and the adhesive or coating in water to form a pulp slurry having adhesive particles dissolved or dispersed in the water, wherein the polymer comprises a polymer

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

having 5 to 40 % of cationic repeat units such that the adhesive or coating is attracted to fibers in the pulp slurry.

Claim 46 (withdrawn): The method of claim 45, further comprising cleaning and screening the repulped paper product to remove contaminants.

Claim 47 (withdrawn): The method of claim 45, wherein the adhesive is substantially tacky such that it forms a pressure-sensitive adhesive which is capable of bonding to a surface upon contact.

Claim 48 (withdrawn): The method of claim 45, wherein the adhesive forms a hot-melt adhesive capable of bonding to a surface when heated to above its melting point temperature.

Claim 49 (withdrawn): The method of claim 45, wherein the polymer comprises a cationically charged monomer and a backbone co-polymerizable with the cationically charged monomer.

Claim 50 (withdrawn): The method of claim 49, wherein the backbone is present in the amount of 60 to 95 mole % based on the polymer.

Claim 51 (withdrawn): The method of claim 49, wherein the backbone is present in the amount of 75 to 85 mole % based on the polymer.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 52 (withdrawn): The method of claim 49, wherein the cationically charged monomer is present in the amount of 10 to 25 mole % based on the polymer.

Claim 53 (withdrawn): The method of claim 49, wherein the backbone is selected from the group consisting of vinyl acetate, butadiene, styrene, acrylate comprising 1 to 8 carbon atoms in the alkyl group, and combinations of these compounds.

Claim 54 (withdrawn): The method of claim 49, wherein the cationically charged monomer is selected from the group consisting of {3-(methacryloylammino)propyl}-trimethyl ammonium chloride, {2-(methacryloyloxy)-ethyl} trimethyl ammonium chloride, diallyldimethylammonium chloride, and vinyl benzyl trimethyl ammonium chloride.

Claim 55 (withdrawn): The method of claim 49, wherein the polymer further comprises an internal cross-linker present in the amount of up to 2 mole % based on the polymer.

Claim 56 (withdrawn): The method of claim 49, wherein the polymer further comprises an internal cross-linker present in the amount of 0.1 to 1 mole % based on the polymer.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER ^{LLP}

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 57 (withdrawn): The method of claim 55, wherein the internal cross-linker is selected from the group consisting of ethylene glycol dimethylether, diallyl maleate, diallyl phthalate, divinyl benzene, and poly(ethylene glycol) di(meth)acrylate.

Claim 58 (withdrawn): The method of claim 53, wherein the back bone is an acrylate selected from the group consisting of alkyl (meth)acrylate, n-butyl acrylate, 2-ethyl hexyl acrylate, and isooctyl acrylate.

Claim 59 (withdrawn): The method of claim 49, wherein the polymer further comprises 0 to 35 mole % based on the polymer of an uncharged water soluble monomer or macromer.

Claim 60 (withdrawn): The method of claim 59, wherein the uncharged water soluble monomer or macromer is selected from the group consisting of , dialkylaminoethyl methacrylate, hydroxy alkyl (meth)acrylate, hydroxy alkyl vinyl ether, poly(ethylene glycol) (meth)acrylate, polyethylene glycol, glycerol, diethylenetriamine, polyethyleneimine, and combinations of these compounds.

Claim 61 (withdrawn): The method of claim 49, wherein the adhesive or coating further comprises a plasticizer to increase the flexibility of the adhesive.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

Claim 62 (withdrawn): The method of claim 49, wherein the adhesive further comprises a tackifier to make the adhesive more tacky.

Claim 63 (withdrawn): A recyclable adhesive tape made according to the method of claim 26.

Claim 64 (withdrawn): A recyclable adhesive label made according to the method of claim 26.

Claim 65 (withdrawn): A recyclable self-adhesive stamp made according to the method of claim 26.

Claim 66 (withdrawn): A recyclable adhesive paper coating made according to the method comprising:

combining a cationically charged monomer of 3-(methacrylamino) propyltrimethyl-ammonium chloride and a backbone of n-butyl acrylate which is copolymerizable with the cationically charged monomer to form a reaction mixture, wherein the concentrations of the cationically charged monomer and the backbone are pre-selected to control the cationic content of the adhesive;

polymerizing the reaction mixture to form a coating comprising a polymer which is soluble or dispersible in water, wherein the polymer has 5 to 40 % of cationic repeat units such that the coating is attracted to fibers during recycling; and

wherein the recyclable coating is for a recyclable paper coating.